



Graver Technologies

Quality Department

**POWDEX[®]
PCN
AMMONIUM FORM**

SPEC NO	GTS-PX3000
REV NO	4
DATE	April 30, 2013

PROPERTIES

Resin Type

Functionality

Matrix

Total Moisture

Total Exchange Capacity

Percent of Sites

Metals (mg/dry kg)

Particle Size Limit

SPECIFICATIONS

Strongly Acidic Cation Exchange Resin

Sulfonic Acid

Styrene-Divinylbenzene

40 - 60%

4.5 meq/dry g (min)

95% Ammonium (min)

10 Copper (max)

50 Iron (max)

50 Sodium (max)

5% > 60 mesh (max)